

Rust-Oleum® Industrial Brands Specification

Coating Specification for Steel Substrates in a Severe Industrial Environment

High Performance 9800 System DTM Urethane Mastic

Specification Prepared by: Rust-Oleum Technical Service, September 2013

This is a general coating specification. Changes to this specification may void any product warranties. Contact your Rust-Oleum representative or Rust-Oleum Technical Service if modifications are required to better meet your needs.



PART I GENERAL

1.01 SCOPE OF WORK

- A.** Provide all materials and labor necessary to install Rust-Oleum 9800 System DTM Urethane Mastic in strict accordance with project drawings, specifications and current Rust-Oleum Corporation application instructions.

1.02 RELATED WORK BY OTHER (SELECT AS NEEDED)

- A.** Division 3 Concrete
- B.** Division 4 Masonry
- C.** Division 5 Metals
- D.** Division 6 Wood
- E.** Division 7 Thermal & Moisture Protection
- F.** Division 10 Specialties
- G.** Division 11 Special Construction

1.03 SYSTEM DESCRIPTION

- A.** The 9800 System DTM Urethane Mastic is a two component, high solids, high build, aliphatic acrylic polyurethane coating system manufactured by Rust-Oleum Corporation, located at 11 Hawthorn Parkway, Vernon Hills, IL 60061 (847) 367-7700. The 9800 System DTM Urethane Mastic is suitable direct to metal application in moderate industrial environments and severe weather exposures. The 9800 System DTM Urethane Mastic consist of selection standard finish colors and tint bases.

1.04 ENGINEERING AND DESIGN REQUIREMENTS

- A.** The Design Architect and Project Engineer shall be responsible for all decisions pertaining to design, detail, and structural capability. Rust-Oleum Corporation has written specifications, technical data and application information to assist in the design and engineering processes.
- B.** Equivalent materials of other manufacturers may be substituted on approval of the engineer or designer. These requests for substitution shall include manufacturer's literature for each product giving the name, resin type, descriptive information, volume solids, and recommended dry film thickness. A list of a minimum of ten (10) projects where the coating system has been applied and performed to expectations for at least three (3) years service is also required. No requests for substitution shall be considered that lower system film thickness, number of coats and/or change the resin type of the specified coating. Equivalent product substitutions will be accepted only from the Contractor and will be considered only after the contract has been awarded.
- C.** Custom colors are available for a nominal charge per color set-up from Rust-Oleum Corporation.
- D.** The 9800 System shall be used only in conformance to the air quality legislation applicable at the location of use.
- E.** The 9800 System is not suitable for water immersion applications.

1.05 SURFACE PREPARATION AND APPLICATION DESCRIPTION

- A.** Substrate cleaning, surface preparation, coating application and dry film thickness shall be as specified and shall meet or exceed Rust-Oleum Corporation's recommendations.

- B. All application equipment shall be clean and maintained in proper working order in accordance with the equipment manufacturers' recommendations.
- C. The 9800 System shall be applied in accordance with the air and surface temperature limits and work areas shall be reasonably free of airborne dust during application and drying time.

1.06 PERFORMANCE REQUIREMENTS

- A. The 9800 System has the following physical properties and these are published on the Rust-Oleum Corporation Technical Data Sheet.

	Finishes*
Volume Solids	58-62%
Recommended Dry Film Thickness (DFT)	3-5 mils
Practical Coverage (assumes 15% material loss)	160-280 sq ft/gal
VOC	<340 g/l (<2.8 lbs/gal)
Mixing Ratio	5:1 base to activator by Volume
Induction Period	None required
Pot Life (@70°F & 50%RH)	2-3 hours
Dry Time (@ 70F/21C and 50% RH)	
Tack Free	4-6 hours
Hard	6-9 hours
Recoat	16-24 hours

* Activated material

1.07 QUALITY ASSURANCE

- A. Applicator Qualifications:
 1. Shall be knowledgeable in the proper installation of 9800 System and experienced in the application of two component systems.
 2. Shall provide a minimum of one (1) year workmanship warranty for the application of the 9800 System.
 3. A list of Certified Rust-Oleum Corporation Coating Applicators is available from Rust-Oleum Corporation.
- B. Pre-, Mid-, and Post-Job Conferences shall be scheduled at discretion of the Project Engineer and/or Design Architect.

1.08 SUBMITTALS

- A. Product Data: 9800 System, application and related equipment information.
- B. Color Cards: Supply color cards of specified materials showing range of colors.
- C. Applicator: If applicable, provide certified contractor documentation showing proof of familiarity with the 9800 System.

1.09 DELIVERY STORAGE AND HANDLING

- A. Deliver the 9800 System on-site in Rust-Oleum Corporation's labeled, original, unopened containers.
- B. All materials shall be stored inside or under cover at ambient temperature. Keep materials dry, protected from elemental damage, and protect from freezing.

1.10 PROJECT CONDITIONS

- A. Protect adjacent work from damage and overspray during application of the 9800 System.
- B. Shop coat primers should be specified to accept the application the 9800 System.

1.11 WARRANTY

- A. The technical data and suggestions of use are correct to the best of our knowledge, and offered in good faith. The statements of this specification do not constitute a warranty, expressed, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.
- B. Special written project warranties may be issued on a request basis at the discretion of the Rust-Oleum Corporation Technical and Legal Departments and would not be contained within this specification document.

2. PRODUCTS

2.01 MANUFACTURER

- A. The 9800 System shall be obtained through a Rust-Oleum distributor. To request nearest distribution source contact Rust-Oleum Corporation.

2.02 MATERIALS

- A. The 9800 System is available in a standard colors, and tint bases for field tinting operations. Contact Rust-Oleum Corporation for availability of colors and container size.

3. EXECUTION

3.01 JOB CONFERENCES

- A. A pre-job conference shall be at the discretion of the architect, engineer or general contractor. Coating contractor, substrate installer and other trades whose work affects the application of the 9800 System shall meet at the project site to review procedures and time schedule proposed for application of the 9800 System and related work. Additional conferences are at the discretion of the architect, engineer, general contractor and/or owner.

3.02 SURFACE PREPARATION

- A. All cleaning and surface preparations specified are minimums.
- B. All surfaces to be coated shall be free of cracks, pits, fins, projections, or other imperfections that would interfere with the formation of a uniform, unbroken coating film.

The coating contractor is to examine the substrate to determine if it is in satisfactory condition to receive the 9800 System. Obtain coating contractor's written report listing conditions detrimental to performance of work in this specification. Do not proceed with the application of the 9800 System until unsatisfactory conditions have been corrected.

- C. All oil, grease, and chalking shall be completely removed with biodegradable degreasers prior to mechanical cleaning begins. (Rust-Oleum 3599 Cleaner Degreaser)
- D. At minimal, all steel surfaces shall be cleaned in accordance to SSPC-SP-3.
- E. Surfaces of welds shall be scraped and ground as necessary to remove all slag and weld spatter.
- F. Previously coated surfaces shall be repaired to be relatively free of surface imperfections. A check for loosely held, delaminating coating shall be performed as per ASTM 3359. The gloss shall be dulled by mechanical means to promote proper adhesion of the Industrial DTM Urethane Mastic. All previous coatings damaged by welding shall be completely removed.
- G. If abrasive blast cleaning is going to be employed, the blasted profile depth shall be uniform and not greater than 20% of final total dry film thickness of the 9800 System.
- H. Satisfactory inspection by the Owner, General Contractor, Project Engineer, at any point in the coating process does not relieve the contractor of ownership and responsibility with regard to application long term service life.

3.03 MIXING AND THINNING

A. MIXING

1. Base component shall be thoroughly mixed prior to the addition of the Activator. Components shall be combined only at the recommended mix ratio.
2. If an optional primer is being used, then thoroughly mix both the base component and activator component separately prior to combining them together.

B. THINNING

1. Thinning shall be done in accordance with applicable local air quality regulations.
2. Thinning of the 9800 System is not required for airless spray, brush, or roller application.
3. Thinning is not normally required for air atomized or HVLP spray. However, the 9800 System can be thinned up to 6% by volume with Rust-Oleum 190 or 333 Thinner.

3.04 APPLICATION

A. Weather Conditions

1. Apply only to a clean and dry surface.
2. Apply when air and surface temperatures are between 40-100° F (5-38° C), the relative humidity is no greater than 85%, and surface temperature is at least 5° F (3° C) above the dew point.
3. The 9800 System shall not be applied, except under shelter, during wet, damp, foggy, or windy weather. When necessary, the area to be coated should be sheltered by a temporary enclosure.

4. If an optional prime coat is to be used, then consult with the Technical Data Sheet for the primer for surface and air temperature requirements.

B. Coating Application

1. Apply two full coat of selected 9800 System finish each at the recommended dry film thickness.
2. Allow a minimum 16 hours .cure time between coats
3. In no instance shall the 9800 System be applied greater than 5 mils dry film thickness per coat.
4. Sags, checks, blisters, skips, teardrops, or rolled edges shall not be accepted and shall be completely removed and recoated.

C. Protection of surfaces

1. The Coating Contractor shall be responsible for protecting all adjacent surfaces from spills, drips, overspray, or any other form of coating damage.
2. The coating contractor and its subcontractors shall be responsible for removing spots or repairing damaged surfaces to the satisfaction of the project engineer, design architect and/or owner.

3.05 CLEAN-UP

- A.** Clean-up shall be done to remove all spills, drips, overspray, or other unwanted coating from all surfaces not intended to be coated.
- B.** All used rags, brushes, roller covers, and other application related materials shall be removed from the work site and disposed in a proper manner and in accordance with local waste regulations.
- C.** All equipment, staging, ladders, and other contractor materials brought onto the jobsite by the contractor shall be remove at the conclusion of the job in a timely manner.

END OF SECTION