•TRUSTED QUALITY SINCE 1921•

RUSTOLEUM°

RUST-OLEUM® CLEAR SHIMMER FLOOR TOPCOAT

DESCRIPTION AND USES

Rust-Oleum® Clear Shimmer Floor Topcoat is a ready-to-use interior/exterior concrete clear protective coating with a decorative shimmer effect, formulated for use on garages, carports, driveways, basements, porches, patios, walkways and pool decks. This product is designed for use over bare concrete or over one-part floor paints such as Rust-Oleum Concrete & Garage Floor Paint + Primer to add a protective, shimmery gloss finish that resists damage from hot tyres, motor oil, grease and gasoline. The durable, UV & weather resistant finish is easy to maintain and resists fading and peeling, and can be easily cleaned up with soap and water.

NOTE: Not recommended for use on asphalt.

PRODUCT FEATURES

- Water-based acrylic
- · Hot tyre and chemical resistant
- For use on garages, driveways, patios and basements

PRODUCT

SKU DESCRIPTION (3.78L)
374277 Clear Shimmer Floor Topcoat

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Whether over bare or previously coated concrete, proper surface preparation is critical to performance. Allow new concrete to cure for a minimum of 28 days. Before coating, if necessary, use a wire brush or sander to remove any loose or unsound concrete or masonry. Remove grease, oil, salt and other contaminants with an appropriate cleaner & degreaser (sold separately). Scrub spots thoroughly with a stiff bristle brush or broom and wipe up excess cleaner with rags or paper towels to keep contaminates from spreading. Rinse thoroughly with fresh water. Repeat as necessary until completely clean.

Bare Concrete Surfaces: For proper penetration and maximum adhesion, use Rust-Oleum Concrete Etch or Rust-Oleum Clean & Etch (sold separately). Follow label instructions carefully and allow the floor to dry completely. Wipe your fingers over the clean, dry surface. If you see any dust or powder on your fingers, repeat scrubbing and rinsing until the floor is clean.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

Previously Painted, Stained or Sealed Concrete Surfaces: Use a wire brush to remove any loose or peeling paint, stain or sealer. To ensure proper adhesion, scuff sand the entire surface and clean with a solvent such as acetone.

For freshly painted surfaces: apply over 1-part water base paints such as Rust-Oleum Concrete & Garage Floor Paint + Primer as a protective clear topcoat without further surface preparation after 24 hours of base coat application and within 7 days.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop.

APPLICATION

Rust-Oleum Clear Shimmer Floor Topcoat is ready to use. Do not thin. Apply only when air (ambient) temperature is between 10-32°C and the relative humidity is below 85%. Do not paint outdoors if rain is expected within 48 hours. If using more than one 3.78L can, intermix (box) all cans of the same product to ensure gloss uniformity. Stir thoroughly before applying.

Use a brush or edger to trim the perimeter and hard-to-reach areas. Use a long handled extension pole and a high quality 10m nap roller cover to apply an even coat of Rust-Oleum Clear Shimmer Floor Topcoat onto the surface. Apply in 1.2m x 1.2m foot sections and maintain a wet edge to prevent lap marks and gloss differences. Continue applying in 1.2m x 1.2m sections until complete. Only one coat is necessary. If a second coat is desired, wait 4 hours before applying the second coat in a direction perpendicular to the first. Occasional touch-up may be necessary for areas subject to heavy vehicle traffic.

NOTE: Painted floors may be slippery when wet. If desired, mix in Rust-Oleum Anti-Skid Additive (sold separately).

DRY & RECOAT TIMES

Dry and recoat times are based on 21°C and 50% relative humidity. Dry times increase at cooler temperatures. The surface should be ready for light foot traffic in 3-4 hours. FOR FULL CURE AND VEHICLE TRAFFIC, ALLOW 5 DAYS.

CLEAN-UP

Wash tools and equipment with warm water and a mild detergent immediately after use. Properly dispose of all soiled rags and protect unused product from freezing.

Form: ARJ-2204 Rev.: 050321



RUST-OLEUM® CLEAR SHIMMER FLOOR TOPCOAT

PHYSICAL PROPERTIES

| | | CLEAR SHIMMER FLOOR TOPCOAT |
|--|--------------|--|
| Resin Type | | Acrylic |
| Pigment Type | | N/A |
| Solvents | | Water, Glycol Ether |
| Weight | Per Gallon | 8.6 lbs. |
| | Per Liter | 1.3 kg |
| Solids | By Weight | 26% |
| | By Volume | 24% |
| Volatile Organic Compounds | | <50 g/l |
| Recommended Dry Film Thickness (DFT) Per Coat | | 1-2 mils |
| | | (25-50µ) |
| Wet Film to Achieve DFT | | 4-8 mils |
| (unthinned material) | | (100-200µ) |
| Practical Coverage at | | 14-23m ² per 3.78L over bare concrete |
| Recommended DFT | | 28-37m ² per 3.78L over coated concrete |
| Dry Times at 21-27°C and 50% Relative Humidity | Recoat | 3-4 hours |
| | Foot Traffic | 3-4 hours |
| | Full Traffic | 5 days |
| Shelf Life | | 3 years |
| Safety Information | | For additional information, see SDS |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



www.rustoleum.com.au

Form: ARJ-2204 Rev.: 050321