

# Rust-Oleum® Industrial Brands Specification

## Coating Specification for Rust-Oleum Virtual Solutions Coating Solution 57

A solvent based coating system

Industrial Choice® 6400 System  
450 VOC DTM Alkyd Enamel

For Steel Substrates in a Mild Industrial Environment

Specification Prepared by: Rust-Oleum Technical Service, March 2011

This is a general coating specification. Changes to this specification may void any product warranties. Contact your Rust-Oleum representative or Rust-Oleum Technical Service if modifications are required to better meet your needs.



## **PART I GENERAL**

### **1.01 SCOPE OF WORK**

- A.** Provide all materials and labor necessary to install Rust-Oleum® Industrial Choice® 6400 System 450 VOC DTM Alkyd Enamel in strict accordance with project drawings, specifications and current Rust-Oleum Corporation application instructions.

### **1.02 RELATED WORK BY OTHER (SELECT AS NEEDED)**

- A.** Division 3 Concrete
- B.** Division 4 Masonry
- C.** Division 5 Metals
- D.** Division 6 Wood
- E.** Division 7 Thermal & Moisture Protection
- F.** Division 10 Specialties
- G.** Division 11 Special Construction

### **1.03 SYSTEM DESCRIPTION**

- A.** The 6400 System 450 VOC DTM Alkyd Enamel is a solvent based alkyd enamel coating system manufactured by Rust-Oleum Corporation, located at 11 Hawthorn Parkway, Vernon Hills, IL 60061 (847) 367-7700. The 6400 System 450 VOC DTM Alkyd Enamel is intended for use in interior, exterior, over properly prepared surfaces in mild to moderate industrial environments. The 6400 System 450 VOC DTM Alkyd Enamel refers to a coating system composed of primers, finishes and tint bases. This coating system is not to be used on galvanized steel.

### **1.04 ENGINEERING AND DESIGN REQUIREMENTS**

- A.** The Design Architect and Project Engineer shall be responsible for all decisions pertaining to design, detail, and structural capability. Rust-Oleum Corporation has written specifications, technical data and application information to assist in the design and engineering processes.
- B.** Equivalent materials of other manufacturers may be substituted on approval of the engineer or designer. These requests for substitution shall include manufacturer's literature for each product giving the name, resin type, descriptive information, volume solids, and recommended dry film thickness. A list of a minimum of ten (10) projects where the coating system has been applied and performed to expectations for at least three (3) years service is also required. No requests for substitution shall be considered that lower system film thickness, number of coats and/or change the resin type of the specified coating. Equivalent product substitutions will be accepted only from the Contractor and will be considered only after the contract has been awarded.
- C.** Custom colors are available for a nominal charge per color set-up from Rust-Oleum Corporation.
- D.** The 6400 System shall be used only in conformance to the air quality legislation applicable at the location of use.

### **1.05 SURFACE PREPARATION AND APPLICATION DESCRIPTION**

- A.** Substrate cleaning, surface preparation, coating application and dry film thickness shall be as specified and shall meet or exceed Rust-Oleum Corporation's recommendations.
- B.** All application equipment shall be clean and maintained in proper working order in accordance with the equipment manufacturers' recommendations.

- C. The 6400 System shall be applied in accordance with the air and surface temperature limits and work areas shall be reasonably free of airborne dust during application and drying time.

#### 1.06 PERFORMANCE REQUIREMENTS

- A. The 6400 System has been tested in accordance to the following test standards. Results are detailed on the Rust-Oleum Corporation Technical Data Sheet.

|                                                | Primer                   | Finishes                 |
|------------------------------------------------|--------------------------|--------------------------|
| Volume Solids                                  | 44%                      | 42-43%                   |
| Recommended Dry Film Thickness (DFT)           | 1-2 mils                 | 1-2 mils                 |
| Practical Coverage (assumes 15% material loss) | 300-600 sq ft/gal        | 285-585 sq ft/gal        |
| VOC                                            | <450 g/l (<3.75 lbs/gal) | <450 g/l (<3.75 lbs/gal) |
| Dry Time @ 70°F/21°C and 50% RH                |                          |                          |
| Tack Free                                      | ½-1 hour                 | 2-4 hours                |
| Handle                                         | 1-2 hours                | 5-9 hours                |
| Recoat                                         | 16-24 hours              | 24 hours                 |

#### 1.07 QUALITY ASSURANCE

- A. Applicator Qualifications:
1. Shall be knowledgeable in the proper installation of the 6400 System and experienced in the application of solvent based alkyd enamel.
  2. Shall provide a minimum of one (1) year workmanship warranty for the application of the 6400 System.
  3. A list of Certified Rust-Oleum Corporation Coating Applicators is available from Rust-Oleum Corporation.
- B. Pre-, Mid-, and Post-Job Conferences shall be scheduled at discretion of the Project Engineer, Design Architect, or General Contractor.

#### 1.08 SUBMITTALS

- A. Product Data: 6400 System, application and related equipment information.
- B. Color Cards: Supply color cards of specified materials showing range of colors.
- C. Applicator: If applicable, provide certified contractor documentation showing proof of familiarity with the 6400 System.

#### 1.09 DELIVERY STORAGE AND HANDLING

- A. Deliver the 6400 System on-site in Rust-Oleum Corporation's labeled, original, unopened containers.
- B. All materials shall be stored inside or under cover at ambient temperature. Keep materials dry, protected from elemental damage, and protect from freezing.

### **1.10 PROJECT CONDITIONS**

- A.** Protect adjacent work from damage and overspray during application of the 6400 System.
- B.** Shop coat primers should be specified to accept the application the 6400 System.

### **1.11 WARRANTY**

- A.** The technical data and suggestions of use are correct to the best of our knowledge, and offered in good faith. The statements of this specification do not constitute a warranty, expressed, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.
- B.** Special written project warranties may be issued on a request basis at the discretion of the Rust-Oleum Corporation Technical and Legal Departments and would not be contained within this specification document.

## **2. PRODUCTS**

### **2.01 MANUFACTURER**

- A.** The 6400 System shall be obtained through a Rust-Oleum distributor. To request nearest distribution source contact Rust-Oleum Corporation.

### **2.02 MATERIALS**

- A.** The 6400 System consist of a selection of primers, a selection of standard color finishes, and tint bases for field tinting operations. Contact Rust-Oleum Corporation for availability of colors and container size.

## **3. EXECUTION**

### **3.01 JOB CONFERENCES**

- A.** A pre-job conference shall be at the discretion of the architect, engineer or general contractor. Coating contractor, substrate installer and other trades whose work affects the application of the 6400 System shall meet at the project site to review procedures and time schedule proposed for application of the 6400 System and related work. Additional conferences are at the discretion of the architect, engineer, general contractor and/or owner.

### **3.02 SURFACE PREPARATION**

- A.** All cleaning and surface preparations specified are minimums.
- B.** All surfaces to be coated shall be free of cracks, pits, fins, projections, or other imperfections that would interfere with the formation of a uniform, unbroken coating film. The coating contractor is to examine the substrate to determine if it is in satisfactory condition to receive the 6400 System. Obtain coating contractor's written report listing conditions detrimental to performance of work in this specification. Do not proceed with the application of the 6400 System until unsatisfactory conditions have been corrected.

- C. All oil, grease, and chalking shall be completely removed with biodegradable degreasers prior to mechanical cleaning begins. (Rust-Oleum 3599 Cleaner Degreaser)
- D. Surfaces of welds shall be scraped and ground as necessary to remove all slag and weld spatter.
- E. At minimum, all steel surfaces shall be cleaned in accordance to SSPC-SP-3 Power Tool Cleaning.
- F. On ferrous metal substrates, if abrasive blast cleaning is going to be employed, the blasted profile depth shall be uniform and not greater than 20% of final total dry film thickness of the 6400 System. Two coats of primer are required on an abrasive blast cleaned substrate.
- G. Previously coated surfaces shall be repaired to be relatively free of surface imperfections. A check for loosely held, delaminating coating shall be performed as per ASTM 3359. The gloss shall be dulled by mechanical means to promote proper adhesion of the 6400 System. All previous coatings damaged by welding shall be completely removed.
- H. Satisfactory inspection by the Owner, General Contractor, Project Engineer, at any point in the coating process does not relieve the contractor of ownership and responsibility with regard to application long term service life.

### **3.03 MIXING AND THINNING**

#### **A. MIXING**

The 6400 System primers and finishes shall be thoroughly mixed to uniform color prior to use.

#### **B. THINNING**

1. Thinning, if needed, shall be done with Rust-Oleum 333 Thinner or a Rust-Oleum recommended substitute solvent.
2. Thinning is generally not required for brush, roll application.
3. Thinning is not normally required for air atomized or HVLP spray. However, the 6400 System can be thinned up to 10-20% by volume if needed.
4. Thin the 6400 System up to 10% by volume for airless spray application.

### **3.04 APPLICATION**

#### **A. Weather Conditions**

1. Apply when air and surface temperatures are between 32-100° F (0-38° C), the relative humidity is no greater than 85%, and surface temperature is at least 5° F (3° C) above the dew point.
2. The 6400 System shall not be applied, except under shelter, during wet, damp, foggy, or windy weather. When necessary, the area to be coated should be sheltered by a temporary enclosure.

#### **B. Coating Application**

1. Edges, corners, seams, welds, bolts, nuts and patch repair areas shall be given a brushed spot coat of primer prior to full coat priming.
2. Apply one full coat of primer within the recommended dry film thickness per coat. A second coat of primer is optional. The primer shall be allowed to cure overnight prior to application of the next coat.

3. Apply two full coats of primer on an abrasive blast cleaned steel substrates.
4. Apply one full coat of selected 6400 System finish at the recommended dry film thickness.
5. The 6400 System shall be recoated no sooner than overnight.
6. Sags, checks, blisters, skips, teardrops, or rolled edges shall not be accepted and shall be completely removed and recoated.

**C. Protection of surfaces**

1. The Coating Contractor shall be responsible for protecting all adjacent surfaces from spills, drips, overspray, or any other form of coating damage.
2. The coating contractor and its subcontractors shall be responsible for removing spots or repairing damaged surfaces to the satisfaction of the project engineer, design architect and/or owner.

**3.05 CLEAN-UP**

- A.** Clean-up shall be done to remove all spills, drips, overspray, or other unwanted coating from all surfaces not intended to be coated.
- B.** All used rags, brushes, roller covers, and other application related materials shall be removed from the work site and disposed in a proper manner and in accordance with local waste regulations.
- C.** All equipment, staging, ladders, and other contractor materials brought onto the jobsite by the contractor shall be remove at the conclusion of the job in a timely manner.

**END OF SECTION**