



ROCKSOLID® FAST PATCH CONCRETE CRACK REPAIR KIT

DESCRIPTION AND USES

RockSolid® Fast Patch is a two-component epoxy putty that is designed to fill minor cracks, spalls, and low spots as well as vertical cracks and slab damage. It does not have to reach full cure to be profiled prior to coating. This makes it ideal for new installers filling hairline cracks, pits and small surface flaws. Fast Patch is the quickest, easiest way to make repairs without the use of any extra equipment.

Excellent for use on garage floors, basements and industrial environments.

FEATURES

- 2-Part epoxy putty
- Easy to mix – 1:1 ratio
- Repairs cracks & minor damage to concrete floors

PRODUCTS

SKU #	Description
303516	Fast Patch

PACKAGING

790 mL

PRODUCT APPLICATION

SURFACE PREPARATION

Surface must be structurally sound, clean and free of dust, dirt, grease, oil, chemical curing compounds and any other foreign materials. Remove contaminants with a heavy-duty degreaser and scrape or wire brush to remove loose concrete and deteriorated coatings. Concrete must be dry before application. Apply when the temperature is between 10-32°C. New concrete must be 28 days old before repairing.

PRODUCT APPLICATION (cont.)

MIXING

Do not thin. Use a clean putty knife to mix equal amounts of Parts A & B on a clean flat piece of cardboard. Mix until a uniform grey putty-like consistency is achieved. Seal containers tightly after use.

APPLICATION

Fast Patch is suitable for application at temperatures between 10°C and 32°C. Use a small putty knife, plastic squeegee or similar tool to fill in cracks, holes, pits, etc. and remove the excess material. Most coatings can be applied directly over the uncured Fast Patch provided repairs are shallow and narrow. For large repairs, allow the Fast Patch to cure fully and then sand with 80 grit sandpaper to profile (de-gloss) the surface before applying coatings. Vacuum to remove all sanding dust.

DRY TIME

Dry time is based on 21°C and 50% relative humidity. The surface will be fully cured in 8-12 hours and suitable for both foot and vehicle traffic in that time.

CLEAN-UP

Clean application tools with xylene.

STORAGE

Keep away from extreme heat, cold and moisture. Maintain a proper storage temperature of 10-32°C. Keep out of direct sunlight and away from fire hazards.

KEEP OUT OF REACH OF CHILDREN AND ANIMALS.



TECHNICAL DATA

ROCKSOLID™ FAST PATCH CONCRETE CRACK REPAIR KIT

PHYSICAL PROPERTIES

Composition		Polyamine cured Epoxy
Solids	By Weight	100%
	By Volume	100%
Mixing Ratio		1:1 part A to part B
Induction Period		None required
Working Time		Up to 30 minutes
Estimated Coverage*		Varies with length and depth of cracks
Dry Times @ 21-27°C (70-80°F) and 50% Relative Humidity	Foot Traffic	8-12 hours
	Vehicle Traffic	8-12 hours
	Full Cure	8-12 hours
Shelf Life		12 months in dry unopened package
Safety Information		See SDS

*Coverage rate is estimated and accounts for material lost when grinding away excess material for a smooth finish.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Australia
Unit 12, 4 Southridge Street
Eastern Creek, NSW 2766
PH: 1 300 784 476
www.rustoleum.com.au
email: sales@rustoleum.com.au

HAYDN BRUSH CO. LTD.
PO Box 4325
Christchurch, New Zealand
PH: 64-3 384 7770
email: mail@haydn.co.nz

Form: GDH-1035
Rev.: 090716