

• TRUSTED QUALITY SINCE 1921 •

RUST-OLEUM®
SPECIALTY**RUST-OLEUM®**
TUB & TILE REFINISHING KIT**DESCRIPTION AND USES**

Rust-Oleum® Specialty Tub & Tile Refinishing kit is a 2-part epoxy acrylic designed to provide excellent adhesion, durability and colour retention in high moisture areas. It is ideal for use to renew ceramic tile and porcelain, fiberglass, acrylic, cast iron and steel tubs and sinks. It is not for use on galvanised steel or flexible plastic. Do not use on areas exposed to extreme heat such as stovetops, or constant high humidity environments. Do not use in continuous water immersion such as swimming pools, hot tubs, ponds, or saunas.

PRODUCT

SKU	DESCRIPTION (946 mL)
385812	Gloss White

PRODUCT APPLICATION**SURFACE PREPARATION**

Remove metal drains and hardware. Remove loose paint and rust with a wire brush or sandpaper. Repair chips and cracks with a patching compound. Remove any mildew with a solution of bleach and water and rinse thoroughly. Scrub dirty or stained surfaces with an abrasive cleaner. Rinse with fresh water and allow to thoroughly dry. Remove all caulk. Wipe area clean. Prepare surface with an abrasive pad and a hard water cleaner. Rinse and repeat if necessary. Sand entire surface with #400/#600 grit wet/dry sandpaper. Vacuum or rinse away any residue. Wipe surface with a tack cloth immediately before painting to remove dust.

WARNING! LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.

PRODUCT APPLICATION (cont.)**APPLICATION**

Use when temperature is between 10-32°C and humidity is below 85% to ensure proper drying. Properly ventilate the area by opening windows or using fans. Thoroughly mix Part B to ensure any settled pigment is re-dispersed. Add Part A to Part B and mix thoroughly for 1 minute. Thin no more than 10% (85mL per 946mL) with 100% isopropyl alcohol (not rubbing alcohol), acetone or xylene. If less than a full (1 quart) kit is needed, mix in a 4:1 ratio of base to activator in a separate container. Apply within 6 hours of mixing.

Brush: Use a fine quality, fine bristle varnish brush. Brush in one direction only for a smooth surface and feather the edges as you paint to avoid a hard line between painted areas. Avoid excessive brushing to ensure an even coat and smooth finish. Apply two coats, waiting at least 1 hour between coats. If necessary, a third coat may be applied the next day with a second kit.

Roller: Use a high quality, 6.4mm short nap roller made for kitchen or bath use. Apply two coats, waiting at least 1 hour between coats. Avoid excessive brushing to ensure an even coat and smooth finish. If necessary, a third coat may be applied the next day with a second kit. If desired, conventional HVLP or airless sprayer may also be used.

DRY and RECOAT TIMES

Based on 21°C and 50% relative humidity. Allow more time at cooler temperatures. Small bubbles will appear on the surface as you paint. As the paint dries, the self leveling properties will eliminate these bubbles. Dries to the touch in 1 hour. Allow to dry at least one hour before applying a second coat. Allow to dry 3 days before exposing to water.

CLEAN-UP

Clean brush and other application tools immediately with lacquer thinner or isopropyl alcohol. Properly dispose of all soiled rags. Properly discard empty container. Do not burn or place in home trash compactor.

	TECHNICAL DATA	SPC-122
• TRUSTED QUALITY SINCE 1921 • RUST-OLEUM® SPECIALTY	RUST-OLEUM® TUB & TILE REFINISHING KIT	

PHYSICAL PROPERTIES

TUB & TILE REFINISHING KIT		
Resin Type		Epoxy Acrylic
Pigment Type		Titanium Dioxide
Solvents		Ethyl Benzene, Light Aromatic Naphtha, Propylene Glycol Monomethyl Ether, 1,2,4-Trimethylbenzene, 1,3,5-Trimethylbenzene, Xylene
Weight	Per Gallon	9.9 lbs.
	Per Liter	1.19 kg
Solids	By Weight	54.6 %
	By Volume	44.4 %
Volatile Organic Compounds		540 g/l (4.50 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.0 mils (37.5-50µ)
Wet Film to Achieve DFT (unthinned material)		3.5-5.0 mils (87.5-125µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		2 coats covers 6.5-10.2m ² /kit or 2 coats on a standard bathtub
Pot Life		Up to 6 hours
Dry Times at 21-27°C and 50% Relative Humidity	Touch	1 hour
	Recoat	1-2 hours
	Full Cure	3 days
Dry Heat Resistance		NA
Shelf Life		3 years
Flash Point		26°C
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



RUST-OLEUM AUSTRALIA & NEW ZEALAND PTY LTD
 Level 2, 307 Ferntree Gully Road
 Mount Waverley, Victoria 3149 Australia
 PH: 1 300 784 476
 Email: technical@rustoleum.com.au
www.rustoleum.com.au

Rust-Oleum New Zealand
 Quad 7 Level 1, 6 Leonard Isitt Drive
 Auckland Airport, Auckland 2022
 New Zealand
 PH: 0800 787 865
 Email: technical@rustoleum.co.nz
www.rustoleum.co.nz

Rust-Oleum South Africa PTY. LTD
 PO Box 400 Randvaal 1873
 Gauteng, South Africa
 PH: 016 365 5120
 Email: info@rustoleum.co.za
www.rustoleum.co.za

Form: ARJ-2539
 Rev.: 100722