

Rust-Oleum® Industrial Brands Specification

Coating Specification for Rust-Oleum Virtual Solutions Coating Solution 52

A 100% solids epoxy coating system

Concrete Protective Systems
8200 System OverKote® TX

For Concrete Floors in Medium Service Areas

Specification Prepared by: Rust-Oleum Technical Service, March 2011

This is a general coating specification. Changes to this specification may void any product warranties. Contact your Rust-Oleum representative or Rust-Oleum Technical Service if modifications are required to better meet your needs.



PART I GENERAL

1.01 SCOPE OF WORK

- A.** Provide all materials and labor necessary to install Rust-Oleum® Concrete Protective Systems 8200 System OverKote® TX in strict accordance with project drawings, specifications and current Rust-Oleum application instructions.

1.02 RELATED WORK BY OTHER (SELECT AS NEEDED)

- A.** Division 3 Concrete
- B.** Division 4 Masonry
- C.** Division 5 Metals
- D.** Division 6 Wood
- E.** Division 7 Thermal & Moisture Protection
- F.** Division 10 Specialties
- G.** Division 11 Special Construction

1.03 SYSTEM DESCRIPTION

- A.** The Concrete Protective Systems 8200 System OverKote® TX is a two component, epoxy coating manufactured by Rust-Oleum Corporation, located at 11 Hawthorn Parkway, Vernon Hills, IL 60061 (847) 367-7700. The Concrete Protective Systems 8200 System OverKote® TX refers to a coating system composed of base component standard colors and an activator. The Concrete Protective Systems 8200 System OverKote® TX develops a heavy textured orange peel finish.

1.04 ENGINEERING AND DESIGN REQUIREMENTS

- A.** The Design Architect and Project Engineer shall be responsible for all decisions pertaining to design, detail, structural capability and the like. Rust-Oleum Corporation has prepared guidelines in the form of specifications, technical data and application information to assist in the design and engineering processes.
- B.** Equivalent materials of other manufacturers may be substituted on approval of the engineer or designer. These requests for substitution shall include manufacturer's literature for each product giving the name, generic type, descriptive information, solids by volume, recommended dry film thickness and a list of a minimum of ten (10) projects where the coating system has been applied and performed to expectations for at least three (3) years service. No requests for substitution shall be considered that lower system film thickness, number of coats and/or offer a change in the generic type of coating herein specified. Requests for review of equivalency will be accepted only from the Contractor and will be considered only after the contract has been awarded. Request for review submitted directly to the Engineer by coating suppliers will not be considered.
- C.** The OverKote TX shall be used only in conformance to the air quality legislation applicable at the location of use.

1.05 SURFACE PREPARATION AND APPLICATION DESCRIPTION

- A.** Substrate cleaning, surface preparation, coating application and dry film thickness shall be as specified herein and shall meet or exceed Rust-Oleum Corporation's recommendations.
- B.** All application equipment shall be clean and maintained in proper working order in accordance with the equipment manufacturer's recommendations.

- C. The OverKote TX shall be applied in accordance with the air and surface temperature limits and work areas shall be reasonably free of airborne dust during application and drying time.

1.06 PERFORMANCE REQUIREMENTS

- A. The OverKote TX has the following physical properties and these are published on the Rust-Oleum Corporation Technical Data Sheet.

	Primer*	OverKote TX*
Solids by Volume	89%	100%
Recommended Dry Film Thickness per Coat (DFT)	6-9 mils	14-16 mils
Practical Coverage @ Recommended DFT (Assumes 15% material loss)	180-260 sq ft/gal	100-120 sq ft/gal
Induction Period	None Required	None Required
Pot Life @70-80°F (21-27°C)	30 minutes	30 minutes
Dry Times @70-80°F (21-27°C) 50% RH Light Traffic Recoat Full Service	NA 6-8 hours NA	10 hours 10-24 hours 48-72 hours

*Activated material

1.07 QUALITY ASSURANCE

- A. Applicator Qualifications:
1. Shall be knowledgeable in the proper installation of OverKote TX and experienced in the application of two component, 100% solids epoxy systems.
 2. Shall provide a minimum of one (1) year workmanship warranty for the application of the OverKote TX.
 3. A list of Certified Rust-Oleum Corporation Coating Applicators is available from Rust-Oleum Corporation.
- B. Pre-, Mid-, and Post-Job Conferences shall be scheduled at discretion of the Project Engineer and/or Design Architect.

1.08 SUBMITTALS

- A. Product Data: OverKote TX, application and related equipment information.
- B. Color Cards: Supply color cards of specified materials showing range of colors.
- C. Applicator: If applicable, provide certified contractor documentation showing proof of familiarity with OverKote TX.

1.09 DELIVERY STORAGE AND HANDLING

- A. Deliver the OverKote TX on-site in Rust-Oleum Corporation's labeled, original, unopened containers.

- B.** Store materials inside or under cover at ambient temperature. Keep materials dry, protected from weather, direct sunlight, surface contamination, aging corrosion, extreme temperatures and other damage.

1.10 PROJECT CONDITIONS

- A.** Protect adjacent work from damage, splash, and spillage during application of the OverKote TX.

1.11 WARRANTY

- A.** The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this specification do not constitute a warranty, expressed, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.
- B.** Special project warranties may be issued on a request basis at the discretion of the Rust-Oleum Corporation Technical and Legal Departments and would not be contained within this specification document.

2. PRODUCTS

2.01 MANUFACTURER

- A.** The OverKote TX shall be obtained through a Rust-Oleum distributor. To request nearest distribution source contact Rust-Oleum Corporation.

2.02 MATERIALS

- A.** The OverKote TX is available in selected standard colors, a Clear and an activator. Contact Rust-Oleum Corporation for availability of colors.

3. EXECUTION

3.01 JOB CONFERENCES

- A.** A pre-job conference shall be at the discretion of the architect, engineer or general contractor. Coating contractor, substrate installer and other trades whose work effects the application of OverKote TX shall meet at the project site to review procedures and time schedule proposed for application of OverKote TX and related work. Additional conferences are at the discretion of the architect, engineer, general contractor and/or owner.

3.02 SURFACE PREPARATION

- A.** All cleaning and surface preparations specified herein are minimums.
- B.** All surfaces to be coated shall be free of cracks, pits, fins, projections, or other imperfections that would interfere with the formation of a uniform, unbroken coating film.
- C.** All oil and grease shall be completely removed with biodegradable degreasers prior to mechanical cleaning begins.

- D. New concrete shall have cured for a minimum 30 days prior to coating application. If a cure and seal agent was added to the concrete or applied after initial cure, the concrete must be abrasive blast cleaned or mechanically abraded to remove the sealer and expose fresh concrete.
- E. Concrete surfaces shall be acid etched, mechanically abraded, or abrasive blast cleaned to remove all laitance to provide a uniform surface profile with a profile depth of 1½ - 3 mils.
- F. The coating contractor is to examine the substrate to determine if it is in satisfactory condition to receive the OverKote TX. Obtain coating contractor's written report listing conditions detrimental to performance of work in this specification. Do not proceed with the application of OverKote TX until unsatisfactory conditions have been corrected.

3.03 MIXING AND THINNING

A. MIXING

1. The base component and activator must be combined with power mixing. Hand mixing is not adequate.
2. Scrape out the container of the activator to transfer as much material as possible.
3. Use a suitable mixing blade which will not entrain air. Mix at 500-750 RPM for 1-3 minutes.
4. Application must begin as soon as the material has been completely mixed.

B. THINNING

1. Thinning is not required. Do not thin.

3.04 APPLICATION

A. Weather Conditions

1. Apply when air and surface temperatures are between 60-80° F (15-27°C) and surface temperature is at least 5° F (3°C) above the dew point.
2. The relative humidity should not be greater than 85%.

B. Coating Application

Note: DO NOT attempt to work out of the container. Immediately after mixing material, pour out the activated material in a long thin stripe across the top of the work section of floor. Use only the material that flows naturally out of the container.

Do not scrape out the container of activated material. Doing so may result with transfer of un-activated material to the floor which will result with soft spots in the coating.

Consult the Rust-Oleum Concrete Protective Systems Product Application Guide for this coating system for complete and detailed application information.

1. Apply Concrete Protective Systems Penetrating Prime & Seal Primer at a rate of one activated gallon per 180-260 sq ft of floor area. Use a rubber squeegee to spread the material over the entire section of floor, then even out the primer by back rolling with a lint free short nap roller cover with a phenolic core. Change roller cover every 30 minutes.

2. Apply OverKote TX at a rate of one activated gallon per 100-120 sq ft of floor area. Use a rubber squeegee to spread the material over the entire section of floor, then even out the OverKote TX by back rolling with a lint free 3/8 nap roller cover with a phenolic core. To establish the texture, make final passes using the Special Texture Roller. Change roller cover every 30 minutes. Exceeding the coverage rate will reduce the texture of the finish.

C. Protection of surfaces

1. The Coating Contractor shall be responsible for protecting all adjacent surfaces from spills, drips, or any other form of coating damage.
2. The coating contractor and its subcontractors shall be responsible for removing spots or repairing damaged surfaces to the satisfaction of the project engineer, design architect and/or owner.

3.05 CLEAN-UP

- A.** Clean-up shall be done to remove all spills, drips, overspray, or other unwanted coating from all surfaces not intended to be coated.
- B.** All used rags, brushes, roller covers, and other application related materials shall be removed from the work site and disposed in a proper manner and in accordance with local waste regulations.
- C.** All equipment, staging, ladders, and other contractor materials brought onto the jobsite by the contractor shall be removed at the conclusion of the job in a timely manner.

END OF SECTION