



RUST-OLEUM® LEAKSEAL® BRUSH

DESCRIPTION AND USES

Rust-Oleum® LeakSeal® Brush is an easy to use, rubberised protective utility coating designed to fill and seal small leaks and cracks. It provides a water-tight, flexible seal that prevents moisture penetration, rust and corrosion. This high-build formula is great for filling large, problematic and hard-to-reach areas. It is suitable for use on metal, aluminum, galvanised metal, PVC, concrete, masonry, asphalt, vinyl siding, fibreglass and more. Not intended for water immersion.

PRODUCTS

| SKU | DESCRIPTION (240 ml) |
|--------|----------------------|
| 279226 | LeakSeal Black |
| 279229 | LeakSeal Clear |

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

PAINTING CONDITIONS

Use outdoors or in a well ventilated area indoors. Use when temperature is between 10-29°C (10-85°F) and humidity is below 85% to ensure proper drying. Do not use on objects that may exceed 93°C (200°F) surface temperature.

SURFACE PREPARATION

Remove dirt and debris from the area to be coated. If necessary, clean the area by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

PRODUCT APPLICATION (cont.)

APPLICATION


Stir product slowly and carefully. DO NOT shake the product. If necessary, thin the material with mineral turps up to 10%. Use a high quality brush and dip into the can slowly (to avoid air bubbles) and apply the product with smooth, light, even strokes. Do not brush over areas that are beginning to dry. Best results are achieved with several light coats versus one heavy coat. If applying with a roller, be sure to use a woven nap roller. Test paint in a hidden area first.

DRY & RECOAT TIMES

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures and higher humidity. Dries to the touch in 30 minutes and can be recoated between 30 minutes and 1 hour. Dries thoroughly after 24 hours.

CLEAN-UP

Clean brush and other tools with mineral turps.

| | | |
|---|--|---------------|
| | TECHNICAL DATA | RLS-03 |
|  | RUST-OLEUM® LEAKSEAL® BRUSH | |

PHYSICAL PROPERTIES

| | | LEAKSEAL BRUSH |
|--|------------|---|
| Resin Type | | Ethylene/Butylene Styrene Polymer |
| Pigment Type | | Black Shading Paste for 279226 |
| Solvents | | N-Butyl Acetate, Aliphatic Hydrocarbons |
| Weight | Per Litre | 0.86 kg |
| | Per Gallon | 7.16 lbs. |
| Solids | By Weight | 26.9% |
| | By Volume | 23.8% |
| Volatile Organic Compounds | | <640 g/l (5.32 lbs./gal.) |
| Recommended Dry Film Thickness (DFT) Per Coat | | 50µ (2 mils) |
| Wet Film to Achieve DFT | | 200µ (8 mils) |
| Theoretical Coverage at 25µ DFT (1 mil) | | 0.60 m²/240 ml (24 sq.ft./one-half pint) |
| Practical Coverage at Recommended DFT | | 0.25 m²/240 ml (10 sq.ft./one-half pint) |
| Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity | Touch | 30 minutes |
| | Recoat | 30 minutes to 1 hour |
| | Fully Dry | After 24 hours |
| Shelf Life | | 2 years |
| Flash Point | | 10°C (50°F) |
| Safety Information | | For additional information, see SDS |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



RUST-OLEUM AUSTRALIA & NEW ZEALAND
PTY LTD
Level 2, 307 Ferntree Gully Road
Mount Waverley, Victoria 3149 Australia
PH: 1 300 784 476
Email: technical@rustoleum.com.au
www.rustoleum.com.au

Rust-Oleum New Zealand
Quad 7 Level 1, 6 Leonard Isitt Drive
Auckland Airport, Auckland 2022 New Zealand
PH: 0800 787 865
Email: technical@rustoleum.co.nz
www.rustoleum.co.nz

Rust-Oleum South Africa PTY. LTD
PO Box 400 Randvaal 1873
Gauteng, South Africa
PH: 016 365 5120
Email: info@rustoleum.co.za
www.rustoleum.co.za

Form: GDH-478
Rev.: 041221