



ULTRA THICK FLOOR FINISH

PROTECT IN JUST ONE COAT

MAXIMUM SCUFF AND SCRATCH RESISTANCE

HIGH TRAFFIC FORMULA

COMPLETE PROJECTS
2X
FASTER

CLEAR SEMI-GLOSS

WATER-BASED

INTERIOR

3.78L

Zinsser® Ultra Thick Floor Finish offers a thicker, stronger and faster project completion than traditional floor varnish. The advanced self-levelling technology allows floor finish projects to be completed in only 2 coats instead of the traditional 3-4 coats. This water-based formula provides exceptional scuff, scratch, and stain resistance with the convenience of soap and water clean-up.

READ ALL DIRECTIONS BEFORE BEGINNING PROJECT.

RECOMMENDED FOR: Interior bare or stained hardwood floors.

NOT RECOMMENDED FOR: Linoleum, vinyl or glazed tiles, metal, or exterior surfaces.

PREVIOUSLY FINISHED SURFACES: For best adhesion, surfaces must be clean, dry and completely free of wax, grease, oil, shellac, lacquer, mildew and polishes. Waxes must be removed with a wax stripper; sanding does not remove wax. Shellac must be removed with a paint stripper. Previously finished floors in good condition should be cleaned with a T.S.P. (Tri Sodium Phosphate) solution in water, and wiped thoroughly with clean water. Do not use T.S.P. on bare wood floors as discolouring will occur. Some types of prefinished or factory finished floors may not be compatible with Zinsser Ultra Thick Floor Finish. Old finishes in poor condition must be removed. Use a floor sander to obtain a smooth surface. Do not use steel wool as rust may develop after the finish has been applied. Remove all sanding dust using a vacuum or cloth dampened with mineral turps.

STAINED OR PAINTED WOOD: Follow manufacturer's direction for application of stain or paint. Make certain surface is thoroughly dry before applying Zinsser Ultra Thick Floor Finish. Refer to manufacturer's label for dry times. For best results, use Zinsser® Wood Stains.

UNFINISHED SURFACE PREPARATION: Using a sander, sand the new wood surface. Remove dust with a rag dampened with mineral turps and a vacuum.

APPLICATION: Stir thoroughly before and during use. To prevent bubbles in the finish, DO NOT SHAKE CONTAINER. Apply using a good quality, synthetic bristle brush, T-bar or shed-free applicator pad. DO NOT USE A ROLLER OR LAMBSWOOL APPLICATOR PAD. Apply additional coats following directions above. Two coats are REQUIRED. If grain raise occurs, sand smooth before final coat.

RECOAT: Allow finish to dry a minimum of 2- 3 hours and then re-coat. Lower temperatures and/or higher humidity may cause slower dry times. Re-coat only when previous coats have dried clear and feel hard. (A powder should develop when lightly sanded.) If any coat has dried more than 24 hours, lightly sand before re-coating.

DRY TIME: Allow finish to dry 24 hours before light use and 7 days for optimal cure.

APPLICATION TIPS: Product appears milky when wet, but dries to a crystal clear coating. Use adequate ventilation at all times. Do not apply in direct sunlight. Apply at temperatures above 13°C and below 32°C. To prevent bubbles in the finish, do not shake container, over-brush or over apply finish. Uneven or inadequate film build will result in an inconsistent appearance, orange peel or stipple. Test Zinsser Ultra Thick Floor Finish in an inconspicuous area before beginning. Testing is particularly important when applying over paints or stains as the appearance of these products may change when a water-based finish is applied.

CLEAN-UP: Soap and water.

COVERAGE: 24 to 30 m² per 3.78m L

CAUTION

KEEP OUT OF REACH OF CHILDREN

DO NOT SWALLOW

FIRST AID INSTRUCTIONS

IF exposed or concerned: Get medical advice. IF exposed or concerned: Get medical advice. IF SWALLOWED: Immediately call a POISON CENTRE (Phone: AUS 13 11 26; NZ 0800 764 766) or doctor. Do NOT induce vomiting. Take off contaminated clothing and wash before reuse. IN CASE OF FIRE: Use alcohol resistant foam or normal protein foam for extinction. IF ON SKIN (or hair): Remove immediately all contaminated clothing. Rinse skin (or hair)with water. IF INHALED: Remove affected person to fresh air and keep at rest in a position comfortable for breathing.

STORAGE: Store locked up. Keep from freezing.

DISPOSAL: Dispose of contents/container in accordance with local regulations.

For further information refer to the Safety Data Sheet available at www.rustoleum.com.au or www.rustoleum.co.nz



©2017 Rust-Oleum Corporation Made in USA 332580 1217

RUST-OLEUM AUSTRALIA PTY. LTD.
Unit 12, 4 Southridge Street
Eastern Creek, NSW 2766 Australia
PH: 1 300 784 476
www.rustoleum.com.au
sales@rustoleum.com.au

HAYDN BRUSH CO. LTD.
PO Box 86054
Christchurch 7675 NZ
PH: 64 3 347 7770
www.rustoleum.co.nz
Info@haydn.co.nz

331386 SEMI-GLOSS ULTRA THICK FLOOR FINISH



332580 1217