

RUST-OLEUM® WET LOOK CONCRETE SEALER

DESCRIPTION AND USES

Rust-Oleum[®] Wet Look Concrete Sealer is a clear water-based sealer designed for interior or exterior use on stained or bare concrete surfaces. It is chemical and abrasion resistant and is resistant to UV sunlight. Wet Look Concrete Sealer is recommended for use on basement floors, concrete and masonry blocks, retaining walls, pavers and stepping stones, statuary and benches. and flower pots.

Wet Look Concrete Sealer is not for use on asphalt and is not recommended for use on garage floors. Use EpoxyShield[®] Premium Clear Coating for garage floors.

PRODUCTS

SKU Description
239416 Gloss Clear (1-Gallon)

PRODUCT APPLICATION

SURFACE PREPARATION

No surface preparation is required if the sealer is being applied to freshly stained concrete.

Clean – Proper surface preparation is critical to performance. Allow new concrete to cure for a minimum of 28 days before applying a stain or sealer. Do not use on asphalt. Remove any oil spots, grease, or spills and wash the floor with EpoxyShield[®] Heavy Duty Degreaser. Scrub thoroughly with a stiff bristle brush or broom. Rinse thoroughly with fresh water. Repeat as necessary to completely clean the surface. If necessary, use a wire brush or sander to remove any loose or unsound concrete or masonry.

Etch - For proper penetration and maximum adhesion on bare concrete and masonry surfaces, use the concentrated citric etch included in the Rust-Oleum Concrete Stain kit or use EpoxyShield Concrete Etch (sold separately). Mix all concentrated citric etch with 2 gallons of water. Mix until dissolved. For best results, use a plastic watering can to evenly distribute solution. Note: Avoid contact with metal (iron, zinc, aluminum) cans. Pre-wet the surface using a hose. Remove pooled water with a squeegee or broom to avoid leaving puddles. Spread the etching solution over a section of the surface. Allow to stand for 1-2 minutes. Scrub with a stiff bristle brush. Keep the entire section wet until it has been completely cleaned and rinsed. Rinse each section thoroughly before starting on the next section. Use a squeegee to remove the rinse water from the surface and to move dirt and contamination away from the work area. Rinse twice before continuing to the next section. Once all sections have been completed, rinse and squeegee the entire surface. A wet/dry vacuum can also be used to remove excess water, dirt and contaminants. Do not leave poled water on the surface. The etching solution will not discolor driveways or harm grass or plants if rinsed thoroughly.

PRODUCT APPLICATION (cont.)

Allow to Dry – Allow the surface to dry completely. Wipe your fingers over the clean, dry concrete. If you see any dust or powder on your fingers, repeat the scrubbing and rinsing process until the concrete is clean. If you fingers remain clean, the surface has been properly prepared and is ready for sealing. Note: If the concrete is not thoroughly etched and completely rinsed, the sealer may not adhere properly to the surface.

APPLICATION

Rust-Oleum Wet Look Concrete Sealer is ready to use. Do not thin. Apply only when air, material, and surface temperatures are between 50-90°F (10-32°C) and the relative humidity is below 85%. Do not apply outdoors if rain is expected within 48 hours. To minimize overspray, properly mask adjacent areas and avoid application in windy conditions. Stir thoroughly before applying. Do not shake. Avoid applying Wet Look Concrete Sealer late in the day when temperatures are falling. The formation of dew can interfere with proper curing. Note: Wet Look Concrete Sealer has a milky appearance when applied but dries to a clear finish. Use a brush to trim the perimeter and hard-to-reach areas. Using a high quality pump sprayer, with the tip set to a fine mist; apply in a circular or figure eight pattern. Make sure the sprayer is fully pressurized. To prevent drips and runs, start and stop the sprayer just off the work area. Apply sealer evenly over the entire surface. On smaller areas, use a hand held trigger sprayer or paint brushes to apply the sealer. Apply two light coats versus one heavy coat. Allow approximately 1 hour dry time between coats. Do not allow the sealer to pool or puddle. Occasional touch-up or recoat may be necessary for areas subject to heavy foot or vehicle traffic.

DRY TIMES

Dries to the touch in 1 hour. Longer dry time is required in cooler temperatures and at higher humidity. Surface is ready for light foot traffic after 24 hours. Allow 72 hours for normal foot traffic, heavy items and automobile traffic. Wait at least 30 days before cleaning with mild detergents.

CLEAN-UP

When finished, wash tools and equipment with warm water. Properly dispose of all soiled rags and protect unused product from freezing.

Form: GDH-78 Rev.: 061313



TECHNICAL DATA

RUST-OLEUM® WET LOOK CONCRETE SEALER

PHYSICAL PROPERTIES

		WET LOOK CONCRETE SEALER
Resin Type		Water-based Acrylic
Pigment Type		None
Solvents		Glycol Ethers, Water
Weight	Per Gallon	8.6 lbs
	Per Liter	1.03 kg
Solids	By Weight	25.2%
	By Volume	23.1%
Volatile Organic Compounds		100 g/l (0.83 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		Penetrating Sealer — No surface film
Wet Film Thickness to Achieve DFT		2 penetrating coats
Theoretical Coverage at 1 mil DFT (25µ)		370 sq.ft./gal. (9.1 m²/l) — depending on concrete porosity
Practical Coverage at Recommended DFT		250-400 sq.ft./gal. (6.2-9.8 m^2 /l) — smooth, bare concrete 170-250 sq.ft./gal. (4.2-6.2 m^2 /l) — rough, porous concrete
Dry Times at 70°F (21°C) and 50% Relative Humidity	Touch	1 hour
	Light Traffic	24 hours
	Heavy Traffic	72 hours
Shelf Life		5 years
Flash Point		>200°F (93°C)
Warning!		CAUTION! MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING VAPORS.AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING.
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

